Profile SHP

CLADDING

Cladding

- Thermally modified
- 6 For exterior and interior use
- Conventional and easy installation
- 6 100% natural, reusable
- High dimensional stability, long-lasting

Additional Features









T&G END-MATCHING, EXCL AYOUS



Thermal modification is a 100% natural method for increasing the durability and dimensional stability of wood, likewise for reducing water absorption. During the process, the wood is heated to a temperature of 180-220°C, while lowering the moisture content of the wood up to 4-6 %. Thermoarena conducts careful quality control of the wood before and after thermal modification. The lumber used for TM is checked and certified.

Technical data

Profile	SHP	m/m^2	m/m^3
	16 x 92	10,87	679
	20 x 92	10,87	543
	20 x 117	8,55	427
	20 x 140	7,14	357
Lenath:	Pine 1.8 - 5.1 m		



Please follow Thermoarena's installation instructions when working with thermal wood











