

Profile HSS

Cladding



- Thermally modified
- For exterior and interior use
- Conventional and easy installation
- 100% natural, reusable
- High dimensional stability, long-lasting

Additional Features



FINISHING



FIRE-RETARDANT
IMPREGNATION



Thermal modification is a 100% natural method for increasing the durability and dimensional stability of wood, likewise for reducing water absorption. During the process, the wood is heated to a temperature of 180-220°C, while lowering the moisture content of the wood up to 4-6 %. Thermoarena conducts careful quality control of the wood before and after thermal modification. The lumber used for TM is checked and certified.

CLADDING

Technical data

Profile	HSS	Coverage m/m ²	in pack m/m ³
pine	42 x 28/42	23,80	567
Length:	Pine 1.8 - 5.1 m		



Please follow Thermoarena's installation instructions when working with thermal wood



Thermoarena

Thermoarena OÜ, Farmi tee 5, Koigi küla, Järva maakond, 72501
Telefon +372 509 6803, info@thermoarena.com, thermoarena.com



The mark of
responsible forestry
FSC® C114364

